

A Critical Synthesis Over Natural Fibers, Include Bamboo and Hemp Flavoured with Glass Fiber Reinforced Plastic



Satya Ranjan Patnaik, Manoj Kumar Pradhan

Abstract: Researchers and academicians are preferably focusing on natural fibers to fabricate in polymer composites for their environmentally friendly and sustainability specialty. The exclusive objective of this review article is to exhibit an inclusive idea of the principal apposite as well as widely used natural fiber reinforced polymer comp

osites (NFPCs) and their purposes. Based on the strand class, basis and construction the possessions of NFPCs differ. This work critically synthesizes the exceptional inherent feature of usual strand taken in a polymeric matrix as an additive, promoting fabrication of inexpensive and insubstantial composites for weight handling structures.

Keywords: Hybridization, hygro-thermal ageing, steam detonation practice, BFRP, decortications, degumming, ligno-cellulosic.

I. INTRODUCTION

In topical time, composites with natural fiber reinforcements (Biswas et. al.) have concerned growing interest since of rising ecological wakefulness. These composites at present measured amongst the utmost suitable resources in the operational group due to explicit machine-driven possessions, recyclability and large quantity [6]. The ordinary fibers methods surpasses the precise mechanical attributes of straight supports, like glass fibers (Thwe et. al.). Accordingly, it is a rising replenishment of concern in the study of fibers which are extracted from non-conventional bases as latent contenders for assistances in qualified composite possessions to substitute the exclusively spread synthetic fibers [9]. The physical distinction, physical attributes, fiber removals, atomic divergence, and temperature relating attributes mold it in a multi-dimensional use in composite-domain [8]. Okubo et al. [10] carried out an explicit observation upon the physical assets of composites considering bamboo fiber

The outcomes explained by Khalil et. al. [7] that the physical attributes of polymer like strength and toughness can be appreciably enhanced in gathering the fibers of bamboo. At the moment, bamboo is measured as a significant plant fiber with immense prospective to be induced in the polymer composite manufacturing. The strands considered here in this current work promotes as an efficient support for fabricating composites with significant weight reduced.

Mitra et al. [12] proposed the specific jute fiber mixed up with liquid-formaldehyde, formaldehyde, melamine formaldehyde and polymerized cashew nut shell, previous to its practice as supporting substantial in fabrication of compounds. The moisture absorbent of the jute can be reduced by this method. Bledzki et. al. [8] reported the fabrication of novel glass reinforced epoxy composites containing phosphate. The distortion through atomic level force interaction of accepted cellulose strand grids and compounds experienced successfully by Amada [2]. It has also been vision that the strengthening augmented the durability of the compound to advanced mass compared with pure polystyrene.

II. GLASS FIBER REINFORCED PLASTICS

The very significant feature of glass fiber reinforcement plastics is that have exceptional thermal and mechanical properties. The intricacy abide with it is to formulate proper dumping method. Since the environmental constraints operating upon the throwing away criteria for glass fiber reinforced plastics (GFRP), then their recycling activity has been meticulously monitored. Based on the inherent configuration of the carbon-carbon intermolecular attachment, the arrangement of organic fiber is projected that their linear string polymer would possess significant potency and solidity. Considering the ecological nature, the synthetic polymer has been overtaken by natural fiber in the industrial submissions. Since the last two decades, the attention has been intensified over the sourcing of budget new materials used in the automotive and aerospace arena [4] and nonetheless natural fiber composite have maintained a position at the top of the list.

Manuscript received on February 10, 2020.

Revised Manuscript received on February 20, 2020.

Manuscript published on March 30, 2020.

* Correspondence Author

Satya Ranjan Patnaik*, Production, BPUT, Rourkela, India.

E-mail: satyaranja.patnaik@gmail.com

Manoj Kumar Pradhan, Mechanical, GITA, Bhubaneswar, India,

E-mail: drpradhan.manoj12@gmail.com.

© The Authors. Published by Blue Eyes Intelligence Engineering and Sciences Publication (BEIESP). This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>)




Fig.1. Glass fiber reinforced plastic

III. HEMP FIBER

It is an ancient plant and known to civilization of nearly 12,000 years of back. It is an indigenous plant of central Asia. During the Iron age it probably spreading over central Europe and there is significance rise of Anglo-Saxons (800-1000AD) in the United Kingdom. Currently, it is developed strongly in China, Philippines, the European Union, and in Central Asia.

The primary ingredients fabricating hemp fibers are cellulose, hemi-cellulose, lignin, and pectin. The corporeal belongings of strands can be put forwarded by the fundamental ingredients like cellulose, hemi-cellulose and lignin. A thorough investigation has been passed by on hemp fiber compounds [5] considering thermo-plastic, thermo-set, and biodegradable polymer matrices. Troedec et. al. [13] investigated that the vital inconvenience over hemp strand compounds are that their water vapor assimilation, surmounted by involving adequate fiber part management. It is recommended that these hemp fibers reinforced epoxy

composites can be used as an alternate material for synthetic fiber reinforced composite materials. The exclusive observation after hemp fiber is that these, strengthen epoxy compounds can replace the synthetic fiber strengthen compounds in the real extent.

Cellulose is one of the resilient and toughest macrobiotic ingredients in the domain of fibers. Conceivably the inconsistency in composition is one of the vital disadvantages of hemp strands which influence the mechanical and physical attributes. As per the fact sheet release from Food and Agriculture Organization (FAO), half of the world's hemp comes from China, where maximum out of the remaining undertaken from France, Chile, the Democratic People's Republic of Korea, and Spain [5].

The rudimentary aspects i.e. thickness and attributes of usual fibers differ noticeably based on the following important criteria such as topographical basis, precipitation during evolution, source, maturity, and score with separating practices.



Fig. 2. Stage Transformations of Natural Hemp Fiber

Okubo et al. [10] experienced a comprehensive investigation through the physical attributes of polypropylene compounds using bamboo strand; based on steam detonation practice. Because of improved impregnation and a significant reduction in empty spaces based on fibers which automatically extracted, there will be a progress of 15 and 30 percent for the ductile forte and the modulus of the polypropylene based composites respectively. Jain et. al. [16] analyzed the influence of fiber essence, fiber span, bambusae upon glass fiber proportion, blend representative (maleic anhydride polypropylene) on ductile and resilient attributes of bambusae strand strengthen polypropylene

(BFRP) and bamboo-glass fiber reinforced polypropylene synthesis complex (BGRP). The exact hybridization with artificial strands is a real-world technique for promoting the physical aspects and the longevity of usual strand compound has been firmly demonstrated. Jain et. al. [16] conceded broad assessment on the durability of bamboo fiber reinforced polypropylene and bamboo-glass fiber reinforced polypropylene subjected to hygro-thermal ageing and weariness conduct viarecurring ductile load.

The proposer acknowledged with certainty that BGRP exhibits superiorunwillingness to ecological maturecompared to that of BFRP.

Considering a certain repeated load average anun-strengthen polypropylene exhibited extended yieldlifespan compared with BFRP and BGRP composites.Also, BGRP,which is a blendcompound, shows an extensible yielding value in comparison to BFRP.

Experimentation conducted by Amada et al. [1] revealed the influence of silane combination representative (Si69) upon remedial feature along with physical attributes of bambusae strand compacted with usual latex compounds exhibit variety aspects. The acknowledgementcomes out as the occurrence by silane combination representative, Si69 advances towards the union amongst the strand and latexbackground and as a result adds to the hardness and tensile modulus, tear strength, tensile strength. Lakkard et al. [11] acknowledged the remedial feature and physical attributes of bambusae strand strengthen usual latex compounds, for the sake of strandstacking, and phenol formaldehyde and amethylene tetramine union representatives. The improvement by the attachment of

bambusae strand upon usual latex has also been experienced. Consequently, the ductile modulus,composite sand solidity raisesthrough filler packing augmentation and the presence of connectingrepresentatives. Athorough investigation [15] has been carried out upon the fabrication and elastic characteristic of bambusae strand strengthen filling coats. The coat has a mix plate coined by bambusae platter and elongated PVA strandstrengthenfillingpane. The outcome through analysis confirmed the elasticfortemagnitudedertainly superior by 90 MPa for coats aside to rearrange bambusae base underneath. The same developed an elastic filmand then strand strengthen filling layer above behaves like a compression layer. Out of the distinguished usualstrands (straw, banana, jute, coir, etc.), bambusae considered reduced compactness and enhanced physical potency. The definite ductileforte and precise gravity of bambusae are apparently lesser to that of glass strands. Nevertheless, economic criteria stand bambusae a striking strand for strengthening. The ductile aspect of date, vakka and bamboo has been observed laterally with the other usual strands namely, sisal, palm,and coconut fibers andbanana.

Table- I: Physico-Mechanical Aspects of UsualStrands

Strand or Fiber	Compactness Or Density (g/cm ³)	Ductile forte or Tensile strength (MPa)	Young's modulus (GPa)	Elongation at break (%)
Bagasse	1.2	20-290	19.7-27.1	1.1
Flax	1.4	88-1500	60-80	1.2-1.6
Hemp	1.48	550-900	70	1.6
Jute	1.46	400-800	10-30	1.8
Coir	1.25	220	6	15-25
Sisal	1.33	600-700	38	2-3
Cotton	1.51	400	12	3-10
Kenaf	1.2	295	-	2.7-6.9
Banana	1.35	355	33.8	53

IV. BAMBOO

A lot of South-East Asian nations, including India, contemplatebambusae as an indispensablemodule of countrysidebudget (TIFAC 2009). Being fewer promoting statussurrounded with augmented development platformbambusaeregisters a vital place in communal forestry arena. With the objective to diminish environmental intricacy over the issue of earthloss and CO₂liberation, bambusae justifies a crucial budgetary asset considering its symbolic genetic layout and environmental implication (Zhou et al., 2005). Considering attribute, bambusae are high, perpetual, arborescent grass, classed to Bambusae, a family under gramineae. Previously the rupture property of bambusae culm and lumps has also been summarized. Bambusae is a phenomenal usualamalgamated substance wherestrands are scattered compactly in the peripheral sections and meagerly within the domain. The very fact against this matter is that the rupture robustness of bambusaeculmsrelies on the quantity of strands. The parts i.e. node and lean sheet of peripheral (bark) of the bambusae are separated where remaining of the echoing cylindrical segment of culm held for removing the strand. A layer of 0.5-1.5 mm thickness along with 10 mm width is extracted

in lengthwise out of the cylindrical segment.The layersended bundled and deepen in aqueous solution for at least three days to become softer. Then it recovered from water, compressed smoothly for the purpose of slacken and to take apart the strand. The consequential strand bundle is fragmented by pointed framedblade and combed. Then the privileged combing and scrapping processes are continued till distinctstrandsbecomedivided. The physically decorticated bamboo fiber strips become dehydrated with the solar radiation. The specific strands detached after the culms graspmattersas well aslatexes. Subsequentlythe process of decorticating, that is dehydratedstrand is extorted through anorganicprocedure of disintegration termedas degumming, where the sticky resources along with the pectin become eliminated. Degumming technique (21) consideredthe foundation for organic withdrawal. Organic withdrawal procedure holds around 33% of strand on considering mass. Previously, the rupture possessions of bambusae culms and lumpsare well experienced. The bambusae evolves as multi-nodes and operatively ascent structure, from both macroscopic andmolecular point of view.After water retention the mechanical properties of bambusae has been observed.



Fig. 3. Stage Transformation of Natural bamboo fiber

V. BAMBOO FIBER

Bamboo vegetations are huge, quick-rising grasslands which possess forested stalks. The individual uniqueness diverges through dimension, augmentation practice, solar forbearance, earth wetness supplement and the degree of hotness / coldness intensity. A number of researchers observed bambusae, a cause of paramount fiber and as a source of roughage from squashing the bamboo. One of payback via bamboo fibers is that it is a plentiful accepted means in the continent like Asia, Middle & South America [11]. This fiber is often recognized as glass fiber owed to its elevated potency based on mass recovered through strands associated longitudinally inside the unit. The ductile forte of bambusae is reasonably intense and may get to a hooping of 370 MPa. This formulates bamboo a striking alternative to steel in tensile loading submissions.

VI. QUALITATIVE SYNTHESIS

A bamboo fiber is a lengthy string includes variety of basic strands, lined with lignin and hemi-cellulose. The average strength has been evaluated with atypical figure of basic strands. It is significant that the ductile potency reduces corresponding to the augmentation of basic strands. The basic strands which considered as the stress supporting foundation within the physical domain respond the improved forte of bamboo strands associated with supplementary accepted strands. The ductile attributes assessed in the current effort are satisfactorily compared with various earlier researchers [11, 12, 13, 20], while the process of withdrawal of bamboo fiber is diverse. Bamboo strings are harder but frailer compare with banana and sisal strands. Vakka strands are harder than sisal but below to that of banana. Vakka strands are so robust associated to banana and sisal strands. Date strings are harder but frailer compare with palm strands. Every strand mentioned in this effort may be cast-off as fortification materials in polymeric composites, based on their use [11]. Amada et al. [1] projected the ductile forte, young's modulus and majority concentration of bamboo package coverings at an expanse of location of culm with the parameter of blend. In reality, a superior fiber may be measured in order to possess a better amount of basic fibers and so there is an augmented prospect of come upon the de-bonding, which appreciably diminishes the stress competence of fiber packages. Consequently, the minute assessment of basic fiber of a bamboo segment can be a substitute way to investigate the fiber asset.

VII. RESULT AND DISCUSSION

The ductile forte obtained by means of a fresh established micro-tensile method is superior than 1.2 GPa, again exceeds 800 MPa of the strand forte found aside to package reference. The course of organic removal diminishes the ductile forte and young's modulus, but augments part tension in contrast to the power-driven method of bamboo fibers. The date character is correspondingly sturdy but elastic when related to bamboo strands. The ductile forte and modulus of sisal fiber [3] projected by numeral nobles diverge from 347 to 700 MPa and from 7 to 22 GPa, correspondingly. It has also been estimated the ductile forte, Young's modulus and compactness of bamboo matrix are 25 MPa, 2 GPa and 1360 kg/m³, and that of untainted character is 810 MPa, 55 GPa and 1050 kg/m³, respectively considering the rule-of-mixtures [13]. The utmost tension out of a hundred, diameter of strands expressed by variety of nobles which differ within 3–14 and 0.05–0.3 mm, considered separately.

VIII. CONCLUSION

Plant strands is basically the diversity of usual strands developed from roots, stalks, leaves, pods and seeds of vegetations. Shrubbery is developed for its aptitude to capitulate strands straight from feral or usual varieties. Basing on business and knowledge, cotton, sisal, flax, palm, coir, arecanut and banana strands get hold of paramount importance. Every ligno-cellulosic grounded usual strand made of roughage micro-fibrils in a shapeless mold of lignin and hemi-cellulose. These strands fabricated of numerous fibrils, which goes all along the span of the fiber: individual fibril reveals intricate covered assembly built up of a slender principal partition encompassing a denser derived layer and looks alike as of a particular timber strand.

REFERENCES

1. Amada S, Muneakata T, Nagase Y, Ichikawa Y, Kirigal A, Yang Z. The mechanical structures of bamboos in view of functionally gradient and composite materials. *J Comput Mater* 1996;30(7):800–19.
2. Amada S, Untao S. Fracture properties of bamboo. *Composites Part B* 2001;32:451–9.
3. Belaadi, A. Bezazi, M. Bouchak, F. Scarpa, Tensile static and fatigue behaviour of sisal fibers, *Mater. Des.* 46 (2013) 76–83.
4. Biswas S, Mittal A, Srikanth G. Development of natural fiber composites in India, *News & Views, TIFAC*. New Delhi: DST; 2005.
5. Eichhorn SJ, Young R J (2003) Composite micromechanics of hemp fibers and epoxy resin microdroplets. *Compos Sci Technol* 63: 1225–1233.

6. Gram H, Person H, Skarendahi A. Natural fiber concrete. Falkoping: GummessonsTryckeri AB; 1984.
7. H. P. S. Abdul Khalil, I. U. H. Bhat, M. Jawaidd, A. Zaidon, D. Hermanwan, Y. S. Hadi, Bamboo fiber reinforced bio-composites: a review, Mater. Des. 42 (2012) 353–368.
8. K. Bledzki, J. Gassan, Composites reinforced with cellulose based fibers, Prog. Polym. Sci. 24 (2) (1999) 221–274.
9. K. M. M. Rao, K. M. Rao, Extraction and tensile properties of natural fibers: Vakka, date and bamboo, Compos. Struct. 77 (3) (2007) 288–295.
10. K. Okubo, T. Fujii, Y. Yamamoto, Development of bamboo-based polymer composites and their mechanical properties, Compos. Part A: Appl. Sci. Manuf. 35 (3) (2004) 377–383.
11. Lakkard S. C, Patel J. M, Mechanical properties of bamboo, a natural composite. J Fiber Sci Tech 1981;14:319–22.
12. Mitra BC, Basak RK, Sarkar M (1998) Studies on jute-reinforced composites, its limitations, and some solutions through chemical modifications of fibers. J Appl Polym Sci 67: 1093-1100.
13. M. Le Troedec, D. Sedan, C. Peyratout et al., “Influence of various chemical treatments on the composition and structure of hemp fibers,” Composites Part A: Applied Science and Manufacturing, vol. 39, no. 3, pp. 514–522, 2008.
14. Nielsen LE (1974) Mechanical properties of Polymers and Composites. Marcell Dekker Inc, New York.
15. N. Defoirdt, S. Biswas, L. De Vriese, L. Q. N Tran, J. Van Acker, Q. Ahsan, et. al., Assessment of the tensile properties of coir, bamboo and jute fiber, Compos. Part A: Appl. Sci. Manuf. 41 (5) (2010) 588–595.
16. S. Jain, R. Kumar, U. C. Jindal, Mechanical behaviour of bamboo and bamboo composite, J. Mater. Sci. 27 (17) (1992) 4598–4604.
17. Thwe M.M., Liao K (2003) Durability of bamboo-glass fiber reinforced polymer matrix hybrid composites. Compos Sci Technol 63: 375-387.
18. TIFAC (Technology Information, Forecasting and Assessment Council), 2009. National Missions on Bamboo Applications (NMBA), India.
19. V. S. Srinivasan, S. R. Boopathy, D. Sangeetha, and B. V. Ramnath, “Evaluation of mechanical and thermal properties of banana-flax based natural fiber composite,” Materials & Design, vol. 60, pp. 620–627, 2014.
20. Zhou, B., Fu, M., Xie, J., Yang, X., Li, Z., 2005. Ecological functions of bamboo forest: research and application. J. For. Res. 16, 143–147.

AUTHORS PROFILE



Satya Ranjan Patnaik, A Ph.d. research scholar in Mechanical Engineering at b.p.u.t., Rourkela, Odisha also presently working as Asst. Professor in the Deptt. Of ME at A.B.I.T., C.D.A., Cuttack, Odisha. Having 14 years of teaching/ research/ industry experience. Has completed M. Tech. in the year 2012 from K.I.I.T., University, Odisha, in

manufacturing process and systems. His research area of interest includes manufacturing of composite materials and its different analysis.



Manoj Kumar Pradhan, A professor and head in the Deptt. Of Mechanical Engineering at G.I.T.A., Bhubaneswar, Odisha. Having 28 years of teaching experiences in post graduates and under graduate students. Has completed M. Tech. in the year 2003 from N.I.T., Rourkela, Odisha, in production engineering, also completed Ph.d. in the year 2012 from Sambalpur University, Odisha.

Has published 27 journal papers. His research area includes manufacturing of composite materials and its different analysis.